

RELATIVE HARDNESS OF SELECTED WOOD FLOORING SPECIES

(ranked by Janka hardness rating)

3840	Patagonian Rosewood
3840	Patagonian Rosewood Red
3670	Lapacho (Brazilian Walnut)
3540	Cumaru (Brazilian Teak)
2450	Red Walnut
2363	Grapia
2350	Brazilian Cherry (Jatoba)
2345	Ivorywood(Brazilian Maple)
2267	Pradoo
2200	Amberwood
2200	Santos Mahogany
2200	Mahogany Rosa
1980	African Rosewood
1854	Kempas
1658	Brazilian Oak
1560	African Teak
1500	Sapele Mahogany
1450	Canadian Maple
1380	Bamboo Natural
1360	White Oak
1320	Ash
1300	Beech
1290	Red Oak
1260	Birch
1180	Bamboo Carbonized
1010	Black Walnut
950	American Cherry